

RE-COATING JOINERY

Joinery has an important advantage: it can be re-coated at any time in its life.

Recoating is like restoring. The aim is to renew the coating film which over the years has lost its gloss but has not yet been irreparably damaged (*no cracks, splits or breaks*). Action must be taken to prevent complete loss of the coating film properties which allow protection of the wood, such as UV radiation absorption or resistance to water or water vapour, since that would result in rapid and sudden deterioration of the unit with the coating coming away and the wood turning grey.



Procedure

Thoroughly clean and degrease the surface. Sand with 220 grit sandpaper, then use a brush or spray to apply waterborne coating Linea Blu **HF 204X** or **HL 206X** in the desired colour all over the unit.

If sanding uncovers bare wood, before the topcoat, apply a local coat of protective wood stain **HI 201X** in the desired colour.



How often

When the coating film needs it.



Materials to be used

220 grit sandpaper, animal/synthetic combination bristle brush or spray gun with nozzle size 2.5 or 3, waterborne transparent topcoat Linea Blu **HF 204X** and protective wood stain Linea Blu **HI 201X** in the desired colour, or waterborne pigmented topcoat Linea Blu **HL 206X** in the desired colour.

