



CLEAR ACRYLIC-POLYURETHANE SELF-SEALER

EXCELLENT LIGHT
PROTECTION

FOR OPEN-PORE
APPLICATIONS

AVAILABLE IN
DIFFERENT OPACITIES



TU75**/00 Clear





CLEAR ACRYLIC-POLYURETHANE SELF-SEALER TU75**/00

TU75/00** is a 2K acrylic-polyurethane self-sealer for interiors, for spray or curtain coater applications on veneered or solid wood.

Available in different levels of opacity - 5, 10 and 25 gloss - the products of the **TU75**/00** series are mainly intended for kitchens and interior furnishings and can be applied both as a primer, directly on wood, then as a finishing.

The main use is in open-pore applications, with systems mainly consisting of just two applications of the same product. After the first coat it is necessary to dry at room temperature for about 3 hours, then sand and apply the second coat.

The **TU75**/00** series has been formulated with innovative resins which, compared to traditional acrylic cycles, provide greater light protection power without the need for UV absorbers.

These characteristics make **TU75**/00** an optimal solution for applications where the prevention of damage caused by UV rays is extremely important, such as those in the nautical sector.

If you wish to further increase the resistance to light for particularly harsh applications, you can consider adding the UV absorber **XTL3465/00** at a rate of 1-3%. However, it is always advisable to check the suitability of the products and carry out a resistance test to light.

TU75/00** can be applied on surfaces painted with **AC1400/XX** water-based or **XM7100/XX** solvent-based dyes.

TECHNICAL FEATURES

AREA OF USE	Open pore coating on veneer and solid wood.								
APPLICATION	Spray gun and curtain coater.								
CATALYSIS AND DILUTION	<table border="0"> <thead> <tr> <th></th> <th>By weight (kg)</th> </tr> </thead> <tbody> <tr> <td>Component A TU75**/00</td> <td>100</td> </tr> <tr> <td>Hardener TH0790/00</td> <td>10</td> </tr> <tr> <td>Thinner DT1150/00</td> <td>30-50</td> </tr> </tbody> </table>		By weight (kg)	Component A TU75**/00	100	Hardener TH0790/00	10	Thinner DT1150/00	30-50
	By weight (kg)								
Component A TU75**/00	100								
Hardener TH0790/00	10								
Thinner DT1150/00	30-50								
AIR DRYING	<table border="0"> <tbody> <tr> <td colspan="2">Air drying (100 g/m² at 20°C):</td> </tr> <tr> <td>Dust free</td> <td>15'-20'</td> </tr> <tr> <td>Touch free</td> <td>40'-50'</td> </tr> <tr> <td>Stackable</td> <td>3 h</td> </tr> </tbody> </table>	Air drying (100 g/m ² at 20°C):		Dust free	15'-20'	Touch free	40'-50'	Stackable	3 h
Air drying (100 g/m ² at 20°C):									
Dust free	15'-20'								
Touch free	40'-50'								
Stackable	3 h								

NOTE: The use of TU75**/00 can be extended to items to be displayed in exterior, increasing the catalysis up to 30% with TH0790/00.

Technical Service: Ph. +39 051 770770 - Fax +39 051 770521 customerservice@sayerlack.com

Sherwin-Williams Italy S.r.l. - Export Department
Via del Fiffo 12 - 40065 Pianoro (BO) - Italy
Ph. +39 051 770511 - Fax +39 051 770528
export@sayerlack.it - www.sayerlack.com



Sayerlack is a brand of The Sherwin Williams Company